

DATA SHEET - APET

PHYSICAL PROPERTIES

CHARACTERISTIC	TEST METHOD	UNIT	LUMEX A VALUE
Density	DIN EN ISO 1183-1	g/cm ³	1.33
Tensile strength	DIN EN ISO 527-1/2	MPa	>55
Flexural modulus	EN ISO 178	MPa	2500
Impact strength, unnotched	ISO 179	kJ/m ²	no break
Surface hardness	ISO 868	Shore D	50
Max. service temperature	–	°C	65
Coefficient of linear expansion	DIN EN ISO 75-2	mm/(m·K)	0.05
Light transmission	DIN 5036	%	>86
Fire classification	EN 13 501-1	Europe	B – s1 – d0

LUMEX® sheets are produced under stringent environmental and quality control procedures. This ensures the consistently high quality of the product.

ROHS DIRECTIVE

LUMEX® sheets meet the requirements of the RoHS-2 directive of the European Union on the restriction of hazardous substances.

REACH REGULATION

LUMEX® sheets meet the requirements of the current version of the European Union chemicals regulation (REACH). In particular, LUMEX® sheets do not contain any of the substances which are listed in the current version of the ECHA Candidate List of "Substances of Very High Concern" (SVHC).